

Report Number : 11/JAN/COA/2936
Customer : Sanderson's Fine Furniture & Joinery Ltd
 Units 1, 5 & 6
 The Village Workshops
 Four crosses
 Powys
 SY22 6ST
Date Received : 19th January 2011
Sample Date :
Date Analysed : 19th January to 3rd February 2011
Report Date : 3rd February 2011
Customer Reference :

Test Method	Sample Reference	Briquette A	Briquette B	Briquette C	Briquette D
SP20 & CA2	Total Moisture %	6.9	7.7	7.5	7.5
CA 3	Ash %	0.4	0.4	0.4	0.5
CA 6	Volatile Matter %	78.1	77.0	77.7	77.1
CA 31	Sulphur %	0.01	0.02	0.01	0.01
*	Chlorine %	0.01	0.01	0.01	0.01
CA 11	Gross Calorific Value kJ/kg	18293	18077	17991	18126
**	Net Calorific Value kJ/kg	16978	16761	16680	16826
CA 9	Carbon %	46.34	45.90	46.09	45.87
CA 9	Hydrogen %	5.26	5.16	5.16	5.10
CA 9	Nitrogen %	0.28	0.26	0.26	0.36
Test results calculated to "As received" Moisture Basis					

TES Bretby does not accept responsibility for the sampling relating to the above results.
 ** calculated using UKAS accredited results.

Report Authorised By
 Jonathan Clay
 (Energy Services Reporting)




1253